



Sabr
Engineering Consultancy
سبر للإستشارات الهندسية

PMA COMPARISON

REPORT CARRIED OUT FOR
DELMON GROUP OF COMPANIES

الرقم :
التاريخ :
الرفقات :

TABLE 1 – SUMMARY

POLYMER	Sample ID	Refinery	% Modifier	Traffic Condition	Jnr at 0.1Kpa	Jnr at 3.2Kpa	Jnr-%Diff	% Recovery at 0.1 Kpa	% Recovery at 3.2 Kpa
PAVEFLEX 140	Paveflex 7.5%	Ras Tanurah	7.5%	Very Heavy	0.389	0.562	44.6	41.6	20.7
	Paveflex 8.0%	Ras Tanurah	8.0%	Very Heavy	0.364	0.552	51.8	44.2	21.6
	Paveflex 7.5%	Riyadh	7.5%	Standard	1.680	2.385	42.0	18.9	3.0
	Paveflex 8.0%	Riyadh	8.0%	Heavy	0.683	1.016	48.7	33.7	11.1
SBS	SBS 4.5%	Ras Tanurah	4.5%	Heavy	1.281	1.977	54.3	34.9	14.5
	SBS 4.0%	Ras Tanurah	4.0%	Standard	2.377	3.291	38.5	18.8	3.6
	SBS 4.5% (1)	Riyadh	4.5%	Standard	2.292	3.231	41.0	14.3	2.2
	SBS 4.5% (2)	Riyadh	4.5%	Standard	2.357	3.017	28.0	14.4	2.9
	SBS 4.5% (3)	Riyadh	4.5%	Standard	2.505	3.279	30.9	13.0	2.7
	SBS 4.0%	Riyadh	4.0%	Standard	3.097	3.981	28.6	7.0	0.0

